

OLYMPIC

Manufacturing process	Tufted		ISO 2424
Gauge	5/32" Loop		
Pilecomposition	100% PP		ISO 2424
Primary backing	Woven PP		ISO 2424
Secondary backing	Felt		ISO 2424
Width	400 cm, 500 cm	± 1%	EN 986
Pile weight	approx. 850 gr/m ²		ISO 8543
Total weight	Felt : approx. 2154 gr/m ²	± 15%	ISO 8543
Pile height	approx. 6,0 mm		ISO 1765
Total height	Felt : approx. 8,5 mm	+ 15% / -10%	ISO 1765
Number of knots	approx. 101.100 /m ²	+ 10% / -7,5%	ISO 1763
Fire classification	Felt : Efl		EN 13501-1
Light fastness	≥ 5		105-B02
Wearability	≥ 4		105-X12
Water fastness	≥ 4		105-E01
Thermal resistance	0,130 m ² K/W		ISO 8302
Sound isulation	20,0 dB		ISO 10140
Pattern repeat	14,3 x 15,1 cm.		
GUT Nr.	Felt : 20DF10F6		

Floorsymbols



Certificates

